



ZHEJIANG KUNHONG NEW MATERIAL CO.,LTD.

Technical data sheet

Model: ET9368

Size: 120x20x3900 mm

Product Name: Wood Plastic Composite Fencing / WPC Fencing

Comosition: 60% Wood Fibres, 30% HDPE & 10% Additives

Test Items	Test Results
Bending Strength: (Joist span 400mm)	25.09 MPA
Modulus of elasticity:	4119 MPA
Maximum load:	2192N
Density:	1.33 g/ cm ³
Brinell Hardness:	58.3 N/mm ²
Rate of Elastic Recovery:	82%
Resistance to Artificial Weathering:	After 2000 hours exposure $\Delta E=0.72$, Grey Scale 4-5
Swelling and Water Absorption (28 days immersion)	4% in thickness 0.8% in width 0.4% in length Water Absorption: 7%
Resistance against Micro-Fungi:	Rate 0, no growth
Linear thermal expansion:	$43.5 \times 10^{-6} / C$
Abrasion Resistance:	Wear Index: 32mg/1000r
Formaldehyde:	Not detected

Product photo:

